

Dzyaloshinskii-Moriya interaction in the paramagnetic state and the polarized neutron scattering.

D.N. Aristov¹, S.V. Maleyev

Petersburg Nuclear Physics Institute, Gatchina 188300, Russia

Abstract

Dzyaloshinskii-Moriya (DM) interaction in the paramagnetic state leads to the incommensurate spin fluctuations with incommensurate vector proportional to the relative strength of the DM interaction. We show that the DM interaction leads to helical spin fluctuations which may be observed by the polarized neutron scattering.

Key words: Dzyaloshinskii-Moriya interaction; Polarized neutron scattering; Quantized spin models.

In the case of inelastic magnetic scattering of polarized neutrons the cross section consists of two terms. The first one is independent on the initial neutron polarization $\mathbf{P}_0$ and determined by the symmetric part of the generalized magnetic susceptibility $\chi_{\alpha\beta}(Q, \omega)$. The second one is proportional to $\mathbf{P}_0$ and connected with the antisymmetric part of $\chi_{\alpha\beta}$. This antisymmetric part of the susceptibility appears if the system is characterized by an axial vector. There are two possibilities. i) External magnetic field or the sample magnetization (see [1,2] and references therein). ii) Some intrinsic axial- vector interaction which is connected to the noncentrosymmetry of the system [3].

In this paper we consider the case of the Dzyaloshinskii-Moriya interaction (DMI) [4] and demonstrate that the dependence of the magnetic scattering on $\mathbf{P}_0$ may appear in the paramagnetic phase along with the incommensurate peaks

in both parts of the scattering cross section. We demonstrate it using the DMI as perturbation in the three-dimensional (3D) case. Then we confirm these results by exact solution of the 1D problem. It should be noted here that the incommensurate $\mathbf{P}_0$ -dependent paramagnetic scattering was observed in MnSi [5]. To the best of our knowledge it is the only experimental study of this problem.

The DMI has the following form [4]

$$V_{DM} = \frac{1}{2} \sum_{l,m} \mathbf{D}_{lm} [\mathbf{S}_l \times \mathbf{S}_m], \quad (1)$$

where $\mathbf{D}_{lm} = -\mathbf{D}_{ml}$ is the DM axial vector. We begin with the case when $\mathbf{D}_{lm}$ is invariant under translations on the lattice, $\mathbf{D}_{lm} = \mathbf{D}_{l+\mathbf{a}_1, m+\mathbf{a}_2}$, and assume that $\mathbf{D}$ is directed along the z axis. After Fourier transform Eq.(1) may be represented as follows

$$V_{DM} = i \sum_{\mathbf{q}} d_{\mathbf{q}} S_{\mathbf{q}}^x S_{-\mathbf{q}}^y, \quad (2)$$

¹ Corresponding author. E-mail: aristov@thd.pnpi.spb.ru

where

$$d_{\mathbf{q}} = -d_{-\mathbf{q}} = -i \sum_l D_{lm} e^{i\mathbf{q}\mathbf{R}_{lm}}. \quad (3)$$

We assume now that the paramagnetic spin fluctuations are isotropic, if one neglects the DMI. In this case the spin Green function has the form $G_{\alpha\beta}^0(q, \omega) = \delta_{\alpha\beta} G^0(q, \omega)$.

Using interaction (2) as small perturbation we obtain

$$\begin{aligned} G_{xx} &= G^0 + iG^0 d_q G_{yx} \\ G_{yx} &= -iG^0 d_q G_{xx}. \end{aligned} \quad (4)$$

As a result we get

$$\begin{aligned} G_{xx} &= G_{yy} = G^0 (1 - d_q^2 (G^0)^2)^{-1} \\ G_{xy} &= -G_{yx} = iG^0 d_q (1 - d_q^2 (G^0)^2)^{-1}. \end{aligned} \quad (5)$$

We see that the DMI leads to the nondiagonal antisymmetric components of the spin Green function. To clarify these expressions let us consider the static approximation ($\omega = 0$) and choose $G(q, 0)$ in the conventional Ornstein-Zernike form

$$G(q, 0) = G(q) = A(q^2 + \kappa^2)^{-1}, \quad (6)$$

where κ is the inverse correlation length and $A \sim (T_c a^2)^{-1}$ where T_c is the transition temperature to the ordered state and a is the interatomic spacing. Having in mind that $d_0 = 0$ and at small q one has $Ad_q = 2\alpha(\mathbf{q}\hat{n})$ where $\hat{n}$ is the direction of the bonds, along which the DM interaction is present, and $\alpha \sim ADa \ll a^{-1}$, we obtain from Eqs. (5) and (6)

$$\begin{aligned} G_{xx} &= G_{yy} = \frac{A}{2} \left(\left[\kappa_1^2 + (\mathbf{q} - \alpha\hat{n})^2 \right]^{-1} \right. \\ &\quad \left. + \left[\kappa_1^2 + (\mathbf{q} + \alpha\hat{n})^2 \right]^{-1} \right), \\ G_{xy} &= -G_{yx} = i\frac{A}{2} \left(\left[\kappa_1^2 + (\mathbf{q} + \alpha\hat{n})^2 \right]^{-1} \right. \\ &\quad \left. - \left[\kappa_1^2 + (\mathbf{q} - \alpha\hat{n})^2 \right]^{-1} \right). \end{aligned} \quad (7)$$

with $\kappa_1^2 = \kappa^2 - \alpha^2$; these expressions describe incommensurate spin fluctuations at $\mathbf{q} = \pm\alpha\hat{n}$.

These expressions are the result of the first order perturbation theory in the DMI value and there should be additional terms of order α^2 in the denominators, which we did not evaluate. According to Ref.[6] due to the DMI the phase transition to the ordered state should be the first order one. Experimental study of this problem would be very interesting. The possible candidates for such study could be the systems MnSi, FeG, Fe₂O₃ and quasi-1D antiferromagnet CsCuCl₃.

As was stated above the antisymmetric part of the spin Green function gives rise to the $\mathbf{P}_0$ -dependent part of the cross section. In our case it may be represented as $G_{\alpha\beta} = i\epsilon_{\alpha\beta\gamma}\hat{z}_\gamma G^A$, where $\hat{z}$ is the unit vector along the z -axis. In this case the $\mathbf{P}_0$ -dependent part of the cross section has the form (cf.[1])

$$\begin{aligned} \left(\frac{d\sigma}{d\Omega d\omega} \right)_{P_0} &= -\frac{2}{\pi} r^2 f^2(q) \frac{k_f}{k_i} (1 - e^{-\omega/T})^{-1} \\ &\quad \times (\mathbf{P}_0 \hat{\mathbf{q}})(\hat{\mathbf{q}} \hat{\mathbf{z}}) \text{Im } G^A(\mathbf{q}, \omega), \end{aligned} \quad (8)$$

where $r^2 = 0.292$ barns, $f(q)$ is the magnetic form-factor and $\hat{\mathbf{q}} = \mathbf{q}/q$.

If the asymmetry of $G_{\alpha\beta}$ is determined by the magnetic field, $\text{Im } G^A$ is an even function of ω and, provided $\omega \ll T$, we have $\int d\omega (d\sigma/d\Omega d\omega)_{P_0} = 0$. It is a consequence of the t -oddness of the magnetic field [1,7]. In our case the vector D is t -even and for the static contribution one has

$$\begin{aligned} \left(\frac{d\sigma}{d\Omega} \right)_{P_0} &= \frac{T}{\pi} A r^2 f^2(q) (\mathbf{P}_0 \hat{\mathbf{q}})(\hat{\mathbf{q}} \hat{\mathbf{z}}) \left[\frac{1}{\kappa_1^2 + (\mathbf{q} + \alpha\hat{n})^2} \right. \\ &\quad \left. - \frac{1}{\kappa_1^2 + (\mathbf{q} - \alpha\hat{n})^2} \right]. \end{aligned} \quad (9)$$

Up to now we discussed the translationally invariant DMI. In the case of the staggered DMI, one has $D_{l+b_x, m+b_y} = -D_{lm}$, where $\mathbf{b}$ is the minimal vector along the bond where the DMI is present. In this case, instead of Eq.(2), we have

$$V_{DM} = i \sum_q d_{\mathbf{q}} S_{\mathbf{q}}^x S_{-\mathbf{q}-\mathbf{k}_0}^y,$$

where $\mathbf{k}_0$ is the AF reciprocal wave vector along $\mathbf{b}$. As a result G_{xy} depends on $\mathbf{q}$ and $\mathbf{q} + \mathbf{k}_0$ and can-

not be determined in the neutron scattering experiments. In this case the cross section is commensurate and independent of $\mathbf{P}_0$.

The above results were obtained in the perturbation theory. We present now an exact solution of the problem in the 1D case. We consider the spin chain Hamiltonian of the form

$$H = \sum_{l=1}^L (J \mathbf{S}_l \mathbf{S}_{l+1} + \mathbf{D} [\mathbf{S}_l \times \mathbf{S}_{l+1}]) \quad (10)$$

with AF Heisenberg coupling $J > 0$ and the Dzyaloshinskii-Moriya term $\mathbf{D}$. It is convenient to introduce here the quantity $\delta = \tan^{-1}(D/J)$.

We observe that H is simplified upon a canonical transformation $H \rightarrow e^{-iU} H e^{iU}$ with $U = \delta \sum_{l=1}^L l S_l^z$. One can easily see that for the combinations $S_j^\pm = S_j^x \pm i S_j^y$ we get

$$\tilde{S}_l^\pm \equiv e^{-iU} S_l^\pm e^{iU} = S_l^\pm e^{\mp i l \delta}, \quad \tilde{S}_l^z = S_l^z, \quad (11)$$

and the Hamiltonian is reduced to the XXZ model:

$$H = \sum_{l=1}^L (J_x (\tilde{S}_l^x \tilde{S}_{l+1}^x + \tilde{S}_l^y \tilde{S}_{l+1}^y) + J \tilde{S}_l^z \tilde{S}_{l+1}^z) \quad (12)$$

with $J_x = J / \cos \delta$. It follows then, that the spectrum of the initial problem (10) coincides with the one of (12). The observables in the initial system are recalculated with the use of (11) from the observables in the XXZ model (12). In the latter model one distinguishes the longitudinal ($G^\parallel(k, \omega)$) and the transverse ($G^\perp(k, \omega)$) spin correlations, for the z and x components of spin, respectively. The difference between these Green functions is small in the considered limit, $\delta \rightarrow 0$.

First we note that U does not affect the z -component of spins. Therefore the “longitudinal” Green function $G_{zz}(k, \omega) = G^\parallel(k, \omega)$ has a commensurate antiferromagnetic modulation.

The transverse spin susceptibilities look a bit more complicated. Some calculation shows that

$$\begin{aligned} G_{xx}(l, m, \omega) &= G_{yy}(l, m, \omega) \\ &= G^\perp(l, m, \omega) \cos \delta(l - m) \\ G_{yx}(l, m, \omega) &= -G_{xy}(l, m, \omega) \end{aligned} \quad (13)$$

$$= G^\perp(l, m, \omega) \sin \delta(l - m) \quad (14)$$

In terms of the Fourier transform this reads as

$$\begin{aligned} G_{xx}(q, \omega) &= G_{yy}(q, \omega) \\ &= \frac{1}{2} [G^\perp(q + \delta, \omega) + G^\perp(q - \delta, \omega)], \\ G_{xy}(q, \omega) &= -G_{yx}(q, \omega) \\ &= \frac{i}{2} [G^\perp(q + \delta, \omega) - G^\perp(q - \delta, \omega)]. \end{aligned}$$

From these expressions we see that the transverse and chiral fluctuations are incommensurate along the chain and in the limit $D/J \ll 1$ the incommensurate vector coincides with that determined by Eq.(7). However the complete solution of the problem (12) can be found in literature (see, e.g., Ref. [8]). In the 1D case we know the exact ω - and q -dependence of all types of the spin fluctuations.

Note that in the quasi-1D compounds the value of $\delta \simeq D/J$, determining the incommensurate wavevector of the fluctuations, may be sufficiently large. For instance, one has $\delta \simeq 0.18$ in the CsCuCl_3 and $\delta \approx 0.05$ in copper benzoate. [9] In the latter compound, however, the presumably staggered variant of DMI should not lead to consequences, observable by the polarized neutron scattering.

In conclusion, we demonstrate that the DM interaction in the paramagnetic state leads to the incommensurate spin fluctuations with incommensurate vector proportional to the strength of the DM interaction relative to the exchange one. It is shown also that DMI leads to the helical spin fluctuations which may be observed by the polarized neutron scattering.

This work was supported by Russian State Program for Statistical Physics (Grant VIII-2), RFBR Grants No. 00-02-16873 and 00-15-96814, and the Russian Program “Neutron Studies of Condensed Matter”.

References

- [1] S.V. Maleyev, Phys.Rev.Lett. **75** (1995) 4682.
- [2] V.P. Plakhty et al., Europhys. Lett. **48** (1999) 215.

- [3] S.W. Lovesey, E. Balkar, Physica B, **267–268** (1999) 221.
- [4] T. Moriya, Phys.Rev. **120** (1960) 91.
- [5] G. Shirane et al., Phys. Rev. B**28** (1983) 6251.
- [6] P. Bak, M. Jensen, J. Phys. C**13** (1980) L881.
- [7] S.V. Maleyev et al., J. Phys. Condens.Matter **10** (1998) 951.
- [8] H.J. Schulz, Phys.Rev. B**34** (1986) 6372.
- [9] U Schotte, A Kelnberger and N Stüsser, J.Phys.: Condens.Matter **10** (1998) 6391; Ian Affleck, M.Oshikawa, Phys.Rev. B**60** (1999) 1038.